

Aquagard M Clear Primer

G P Primer for Elastomeric Polyurethane Membranes

Description

A fast drying, stable, single pack, modified polyurethane pre-polymer concrete primer for use with all Chemind polyurethane based membranes and Chemspray 750.

Uses

Aquagard M Clear Primer is used for all polyurethane based Chemind membranes including: Aquagard M – all grades, Proflex TF, Acoustiflex and Bituthene Mastic Membrane.

It may be applied to most rigid substrates used in construction including: concrete masonry, off-form concrete, in-situ concrete slabs and topping, shotcrete and cement render, light-weight foamed concrete, pre-cast concrete panels, compressed fibre cement sheet, metal and brick.

Features

- Strong physical bond to substrate
- Fast drying PU resin system
- Coating is water-resistant and protects the structure in the event of interruption by wet weather
- Promotes adhesion even in cold weather

Typical Properties

Colour	Clear
S.G.	0.9-1.0 g/ml
Viscosity	500cPs
Water Resistance	Excellent
Drying Time @ 20°C	20 - 30 minutes

Preparation

Surfaces must be clean, dry and free from dust, loose matter, oil or other contaminants.

Application

Apply one coat directly from container using brush, roller or spray. Allow primer coating to become tack free before applying waterproof membrane system.

Apply selected Chemind polyurethane product in strict accordance with product instructions.

NOTE

- Use Chemind Epocote F100 W as primer on damp, green or solvent sensitive surfaces.
- Aquagard M Clear Primer is flammable.
- Care should be exercised in the application of Aquagard M Clear Primer in any confined space.
- Consult product MSDS and use PPE and/or ventilation if required.

Coverage

Application rate is approx 6 - 8m²/kg.

Packaging

Aquagard M Clear Primer is packed in 17kg metal pails.

Clean Up

Use Chemind GP Solvent or methylated spirits before curing. Exercise care when using solvent, review all MSDS before use.

Storage

Store unopened containers in a cool dry place. Keep away from any fire hazards or ignition sources.

Shelf Life

Stored in a cool, dry place unopened cans have a shelf life of 12 months.



HEAD OFFICE
74 Annie Street
ROCKLEA QLD 4106
AUSTRALIA
Ph: (+617) 3255 5755
Fax: (+617) 3255 5991
ABN: 63 250 804 992