

Sarnafil® G 410-20EL FELT 200g

Polymeric sheet for roof waterproofing

Product Description Sarnafil® G 410-20EL FELT 200g (thickness 2.0 mm) is a multi-layer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) with inlay of glass non-woven and polyester fleece backing.

Uses Waterproofing membrane for:
 ■ Fully adhered roofs

Product Data

| | | |
|---|-------------------------------------|--|
| Visible defects | Pass | EN 1850-2 |
| Length | 15 (-0 / +5 %) m | EN 1848-2 |
| Width | 2 (-0.5 / +1 %) m | EN 1848-2 |
| Straightness | ≤ 30 mm | EN 1848-2 |
| Flatness | ≤ 10 mm | EN 1848-2 |
| Effective thickness | 2 (-5 / + 10 %) mm | EN 1849-2 |
| Mass per unit area | 2.8 (-5 / + 10 %) kg/m ² | EN 1849-2 |
| Water tightness | Pass | EN 1928 |
| Effects of liquid chemicals, including water | On request | EN 1847 |
| Reaction to fire | E | EN ISO 11925-2 , classification after EN 13501-1 |
| Hail resistance: | | EN 13583 |
| rigid substrate | ≥ 28 m/s | |
| flexible substrate | ≥ 36 m/s | |
| Joint peel resistance | ≥ 300 N/50 mm | EN 12316-2 |
| Joint shear resistance | ≥ 500 N/50 mm | EN 12317-2 |
| Water vapour transmission properties | μ= 15'000 | EN 1931 |
| Tensile strength, | | EN 12311-2 |
| longitudinal (md)* | ≥ 800 N/50 mm | |
| transversal (cmd)* | ≥ 800 N/50 mm | |

Roofing



Roofing

| | | |
|---------------------------------------|-----------------|------------|
| Elongation, | | EN 12311-2 |
| longitudinal (md)* | ≥ 65 % | |
| transversal (cmd)* | ≥ 65 % | |
| Resistance to impact, | | EN 12691 |
| hard substrate | ≥ 900 mm | |
| soft substrate | ≥ 1500 mm | |
| Dimension stability, | | EN 1107-2 |
| longitudinal (md)* | ≤ 0.2 % | |
| transversal (cmd)* | ≤ 0.1 % | |
| Foldability at low temperature | ≤ -25 °C | EN 495-5 |
| UV exposure | Pass (> 5000 h) | EN 1297 |

*md = machine direction

*cmd = cross machine direction

Legal disclaimer: The information, and, in particular, the recommendations relating to the application and end-use of Sika® products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sarnafil Waterproofing systems (Shanghai) Ltd.
No.4555 Hua Ning Rd.Xinzhuang Industry Park
Shanghai 201108,China

Phone +86 21 34073788
Fax +86 21 34073788
www.sarnafil.com.cn

Sarnafil®