

# Sarnacol 606

## Polyurethane based fluid adhesive

Construction

|  |   |
|--|---|
| <b>Description</b>   | Sarnacol 606 is a one component Polyurethane based light blue fluid adhesive.   |
| <b>Properties</b>  |   |
| <b>Material</b>  | Polyurethane  |
| <b>Colour</b>  | Light Blue  |
| <b>Viscosity</b>   | 1400-2000 mPa.s   |
| <b>Solid Content</b>   | 12-18%  |
| <b>Shear Strength (Standard Condition)</b>   | ≥ 1.8N/mm   |
| <b>Holding rate of Shear Strength after heat treatment (80°C, 168h)</b>                    | ≥ 70%   |
| <b>Holding rate of Shear Strength after Alkali treatment (10%Ca(OH)<sub>2</sub>, 168h)</b> | ≥ 70%   |
| Product Standard: JC 863-2000, China industry standard                                     |   |
| <b>Application</b>   | Sarnacol 606 is used for adhesion of Sarnafil membrane PVC surface to PVC surface, or Sarnafil membrane PVC surface to upstand substrates like concrete, screed and steel deck up to Sarnafil requirements.   |
| <b>Packaging</b>   | 18 kg drum  |
| <b>Shelf life &amp; Storage</b>  | 12 months if stored in warehouse under the condition of 0-40°C. Store away from fire sources.   |
| <b>Important Notice</b>  | <ul style="list-style-type: none"> <li>• This product should be away from fire sources during transportation, storage and application.</li> <li>• The working temperature should be higher than 5°C.</li> <li>• The surface should be clean, dry, smooth and strong.</li> <li>• Apply the product on both surfaces to be bonded, after surface dry of the adhesive coat (about 10 min.) adhesion can be carried out.</li> </ul>   |
| <b>Important Notification</b>  | <p>The information, and, in particular, the recommendations relating to the application and end-use of Sika's products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject of our terms and conditions of sale. Users should always refer to the most recent issue of the Australian version of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.</p> <p>PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.</p> |

